

Product Information

Dolit^{LC}

BL.PH.001 | 04/12/2023



PRODUCT GROUP

Coatings Laminate

BINDER BASE

Phenolic resin

PROPERTIES / APPLICATION

Crack-bridging laminate system based on a modified phenolic resin for application on primed steel and concrete surfaces or on a Dolit Acid protection membrane.

Wide applicability as a coating system with high chemical resistance, especially to acids and solvents (as well as chlorinated hydrocarbons and methylene chloride).

- Temperature resistance
 - Up to 60 °C on concrete.
 - Up to 90 °C dry load on steel (direct stress on the laminate).
 - The temperature resistance is basically dependent on the project-specific chemical stress.
- Very high chemical resistance to a wide range of media, such as various inorganic and organic acids, greases, oils and fuels, solvents and various chlorinated hydrocarbons.
- Can be used inside buildings or outdoors.
- Depending on requirements, Glass-Fibre-Mat 450 g/m² can also be used instead of Glass-Fibre-Mat 300 g/m².
- Electrically conductive adjustable by using Dolit-Hybrid-Fleece 20L.

SYSTEM DESIGN

On concrete

- Dolit 848 Primer
- Dolit VE Barrier layer
- Sprinkling Dolit-Filler 15
- Dolit CN Scraper Coat
- Dolit LC Laminate Concrete (2 x Glass-Fibre-Mat 450 g/m² + Glass-Fleece 30 g/m² in Dolit LC Laminating Solution)

Layer thickness ≈ 3 mm

On steel

- 2 x Dolit VE Barrier layer
- Dolit LC Laminate Steel (2 x Glass-Fibre-Mat 450 g/m² + Glass-Fleece 30 g/m² in Dolit LC Laminating Solution Steel)

Layer thickness ≈ 2 mm

The coating can be made dissipative by using Dolit-Hybrid-Fleece 20L instead of Glass-Fleece 30 g/m².



PHYSICAL DATA

Physical property	DIN	ASTM	Value	Unit
Shore D hardness	DIN 53505	ASTM D 2240	> 60	Shore D
Adhesive strength to steel	DIN EN ISO 4624		> 2	MPa
Adhesive strength to concrete/screed	DIN EN ISO 4624		> Inherent tensile strength	MPa
Electr. leakage resistance (when Dolit-Hybrid-Fleece 20L is used)	DIN EN 14879-3 At >70% relative humidity	ASTM F 150/98	≤ 10 ⁶	Ω

PRECONDITIONS

The temperatures for the substrate, ambient air and Dolit materials must be between 15 °C and 30 °C during application. The optimum processing temperature is 20 °C. Higher and lower temperatures affect the working time and consistency of the composition. Consumption and application performance may change as a result.

During application, the substrate must be kept absolutely dry. No moisture (condensate, mist, etc.) may get onto the surfaces to be protected.

Unevenness must already be levelled out in the substrate.

Distance to dew point has to be at least 3 K, at a relative humidity of above 70 % at least 5 K.

The construction site must be protected from draught and direct sunlight.

CONCRETE / SCREED

Refer to DIN EN14879-1.

The substrate must be pretreated to achieve sufficient adhesive tensile strength. It must be free from cement slurry, cement skin, loose and friable parts, structural defects and separating substances.

The residual moisture of cementitious substrates must not exceed 4 %.

The effect of water or water vapour pressure on the back of the coating/lining must be prevented.

STEEL

Refer to DIN EN14879-1.

The steel surface is blasted to near white blast cleaning. A surface cleanliness of Sa 2½ according to DIN EN ISO 12944-4 and the roughness grade "Medium (G)" according to DIN EN ISO 8503-1; minimum surface roughness R_z = 70 µm must be achieved. After blasting, the reformation of rust must be prevented by suitable measures.

Product Information

Dolit^{LC}

BL.PH.001 | 04/12/2023



DELIVERY FORM / BEST BEFORE DATE

Component	Item no.	Quantity	Package	Months
Dolit-848-Solution	5235290001	25 kg	Hobbock	24
Dolit-848-Hardener	5235288017	12.5 kg	Drum	24
Dolit-VE-Solution	5232003001	25 kg	Hobbock	6
Dolit-VE-Accelerator	5232001023	2.5 kg	Can	24
Dolit-VE-Hardener	5232002007	1 kg	Bottle	12
Dolit-Filler 15	5211202001	25 kg	Bag	24
Dolit-CN-Solution	5233005001	25 kg	Hobbock	12
Dolit-CN-Powder	5233045021	15 kg	Bag	24
Glass-Fibre-Mat 450 g/m ² W=127cm L=80m	9300900388	102 m ²	Roll	unlimited
Dolit-LC-Solution	5233013001	25 kg	Hobbock	12
Dolit-LC-Hardener	5233012006	10 kg	Canister	24
Glass-Fleece 30 g/m ² W=100cm	9300900089	250 m ²	Roll	unlimited
Dolit-Hybrid-Fleece 20L	5219020003		Roll	unlimited
Cab-O-Sil TS 720	5011016044	0.5 kg	Bag	24

- All components must be stored and transported in a dry and frost-free place.
- The minimum shelf life applies to a storage temperature of 20 °C. Higher temperatures shorten, lower temperatures extend the minimum shelf life.

Safety notice

- For handling, storage and transport, observe the relevant safety data sheets!

WORKING EQUIPMENT

NOTE!

The materials to be processed can have an aggressive effect on mixing and processing tools due to the solvents, acidic, alkaline or abrasive components they contain. Therefore, please use only suitable tools for mixing and processing.

Measuring cup

Scale

Mixing vessel

Drilling machine

Anchor stirrer

Paint roller

Brush

Disk roller

Scissors

Laminating brush

Special colour roller 9703640123

Metal smoothing trowel

Product Information

Dolit^{LC}

BL.PH.001 | 04/12/2023



CRS
Chemical Resistant Systems

GISCODE

Product	GISCODE
Dolit 848 Primer	RE80
Dolit VE Barrier layer	SB-STY20
Dolit CN Scraper Coat	SB-P30
Dolit LC Laminate Concrete, Dolit LC Laminate Steel	SB-P 40

MIXING RATIO / CONSUMPTION

CONCRETE

PRIMER

Dolit 848 Primer

Component	kg per m ²	Part by weight	kg per Mix	Liters per Mix
Dolit-848-Solution	0.200	100	2.000	1.800
Dolit-848-Hardener	0.100	50	1.000	1.000
Total	0.300	150	3.000	

Area per batch	≈ 10 m ²
----------------	---------------------

Dolit VE Barrier layer

Component	kg per m ²	Part by weight	kg per Mix	Liters per Mix
Dolit-VE-Solution	0.281	100	2.180	2.000
Dolit-VE-Accelerator	0.006	2	0.045	0.045
Dolit-VE-Hardener	0.007	2.5	0.055	0.055
Cab-O-Sil TS 720	0.006	2	0.045	0.900
Total	0.300	106.5	2.325	

Area per batch	≈ 7.75 m ²
----------------	-----------------------

Sprinkling Dolit-Filler 15

Component	kg per m ²
Dolit-Filler 15	0.500

SCRAPER COAT

Dolit CN Scraper Coat

Component	kg per m ²	Part by weight	kg per Mix	Liters per Mix
Dolit-CN-Solution	0.720	100	2.000	1.650
Dolit-CN-Powder	1.080	150	3.000	4.320
Total	1.800	250	5.000	

18014405864177163 • V 3 • en

www.dolit-crs.de

Product Information

Dolit^{LC}

BL.PH.001 | 04/12/2023



CRS
Chemical Resistant Systems

Area per batch	≈ 2.8 m ²
----------------	----------------------

LAMINATE

NOTE!

Depending on the project-specific geometry, additional consumption for mats, fleece and solution must be planned due to the overlapping of the glass fibre materials.

Dolit LC Laminating Solution

Component	kg per m ²	Part by weight	kg per Mix	Liters per Mix
Dolit-LC-Solution	1.725	100	10.000	8.300
Dolit-LC-Hardener	0.275	16	1.600	1.350
Total	2.000	116	11.600	

Area per batch	≈ 5.8 m ²
----------------	----------------------

NOTE!

To achieve better stability on wall surfaces, 1 part Cab-O-Sil TS720 can be added to the Dolit LC laminating solution per 100 parts by weight (corresponds to 2.4 l or 0.12 kg per batch).

Glass-Fibre-Mat 450 g/m²

Component	m ²
Glass-Fibre-Mat 450 g/m ²	2.2

Glass-Fleece 30 g/m²

Component	m ²
Glass-Fleece 30 g/m ²	1.1

Alternative - conductive laminate

Component	m ²
Dolit-Hybrid-Fleece 20L	1.1

STEEL

DOLIT VE BARRIER LAYER ON STEEL

Dolit VE Barrier layer apply 2 x 0.300 kg/m² each. Total consumption: 0.600 kg/m²

Dolit VE Barrier layer

Component	kg per m ²	Part by weight	kg per Mix	Liters per Mix
Dolit-VE-Solution	0.281	100	2.180	2.000
Dolit-VE-Accelerator	0.006	2	0.045	0.045
Dolit-VE-Hardener	0.007	2.5	0.055	0.055
Cab-O-Sil TS 720	0.006	2	0.045	0.900
Total	0.300	106.5	2.325	

Area per batch	≈ 7.75 m ²
----------------	-----------------------

Product Information

Dolit^{LC}

BL.PH.001 | 04/12/2023



CRS
Chemical Resistant Systems

LAMINATE

NOTE! Depending on the project-specific geometry, additional consumption for mats, fleece and solution must be planned due to the overlapping of the glass fibre materials.

Dolit LC Laminating Solution Steel

Component	kg per m ²	Part by weight	kg per Mix	Liters per Mix
Dolit-LC-Solution	1.900	100	10.000	8.300
Dolit-LC-Hardener	0.300	16	1.600	1.350
Total	2.200	116	11.600	

Area per batch	≈ 5.2 m ²
----------------	----------------------

NOTE! To achieve better stability on wall surfaces, 1 part Cab-O-Sil TS720 can be added to Dolit LC Laminating Solution Steel per 100 parts by weight (corresponds to 2.4 l or 0.12 kg per batch).

Glass-Fibre-Mat 450 g/m²

Component	m ²
Glass-Fibre-Mat 450 g/m ²	2.2

Glass-Fleece 30 g/m²

Component	m ²
Glass-Fleece 30 g/m ²	1.1

Alternative - conductive laminate

Component	m ²
Dolit-Hybrid-Fleece 20L	1.1

MIXING / APPLICATION

Processing may only be started when the application requirements are met and can be maintained during the entire processing and curing.

Scattered surfaces should be lightly sanded over after curing. In any case, the surface must be carefully cleaned of loose material before applying further coats.

MIXING SEQUENCE



DANGER

The mixing sequence for VE systems must be strictly adhered to, otherwise there is a risk of explosion!



Mixing sequence for Dolit VE barrier layer

- Liquid components are measured or weighed out.
- First add Dolit-VE-Solution to the mixing vessel.
- Then add Dolit-VE-Accelerator and stir carefully with an anchor stirrer (300 - 500 rpm) to a homogeneous solution.
- Only then add Dolit-VE-Hardener and mix again carefully until a homogeneous solution is formed.
- Move the stirrer past the vessel wall and bottom.

Mixing sequence for other components

- Stir solutions well with an anchor stirrer (300 - 500 rpm) before use or partial withdrawal. Move the stirrer past the vessel wall and bottom.
- Liquid components are measured or weighed out, transferred to a mixing vessel and carefully stirred.
- Mix the components with a drill and an anchor stirrer (300 - 500 rpm) to a homogeneous solution. Move the stirrer past the vessel wall and bottom.
- Solids are measured or weighed out individually, added to the solution in portions and mixed in carefully until a lump-free mixture is obtained.

APPLICATION

CONCRETE

Primer

- Dolit 848 Primer apply with paint roller or brush. No puddles must be left in concrete depressions or expansion joints.

Barrier layer

- Apply the Dolit VE Barrier layer with a paint roller or brush. No puddles must be left in concrete depressions or expansion joints.
- Sprinkle the fresh barrier layer with Dolit-Filler 15.
- After curing, excess Dolit-Filler 15 is removed.

Scraper Coat

- Apply the filling mass to the primed substrate in the desired thickness with a metall smoothing trowel. Trowel marks and ridges are to be avoided.

Laminate

- Embed the Glass-Fibre-Mat 450 g/m² freshly into the Dolit CN Scraper Coat in two layers one after the other with the necessary overlap (approx. 5 cm).
- Press on each layer individually with the disc roller and apply Dolit LC Laminating Solution with the special paint roller 9703640123.
- Each layer is vented with the disc roller.
- The seams of the individual layers are to be staggered by 20 cm.
- If not all layers can be applied in one work step, apply Dolit LC Laminating Solution again after the surface is tack-free and continue working as described.
- The final layer Glass-Fleece 30 g/m² must always be applied together with the underlying Glass-Fibre-Mat 450 g/m².



STEEL

Barrier layer

- Apply the Dolit VE Barrier layer with a paint roller or brush. No puddles must be left in concrete depressions or expansion joints.
- After the first coat has hardened, a second coat Dolit VE Barrier layer is applied.

Laminate

- Apply to the hardened Dolit VE Barrier layer with the special colour roller 9703640123 Dolit LC Laminating Solution Steel.
- Freshly embed the Glass-Fibre-Mat 450 g/m² in two layers one after the other with the necessary overlap (approx. 5 cm).
- Press on each layer individually with the disc roller and apply Dolit LC Laminating Solution Steel with the special paint roller 9703640123.
- Each layer is vented with the disc roller.
- The seams of the individual layers are to be staggered by 20 cm.
- If not all layers can be applied in one work step, apply Dolit LC Laminating Solution Steel again after the surface is tack-free and continue working as described.
- The final layer Glass-Fleece 30 g/m² must always be applied together with the underlying Glass-Fibre-Mat 450 g/m².

POT LIFE

- The pot life depend on the temperature and are as follows at 20 °C.

Dolit 848 Primer	Dolit VE Barrier layer	Dolit CN Scraper Coat	Dolit LC Laminating Solution
60 – 120 min	≈ 40 min	≈ 60 min	≈ 30 min

WAIT- / CURING TIME

The minimum waiting time before further processing and the maximum waiting time between working steps are at 20 °C.

Layer	Until further processing	Maximum waiting time
Dolit 848 Primer	16 h	14 d
Dolit VE Barrier layer (for 2nd primer)	3 h	78 h
Dolit VE Barrier layer (for CN scraper coat/laminate)	3 h	14 d
Dolit LC Laminate (e.g. for subsequent layers based on phenolic resins)	24 h	48 h

The finished coating is fully mechanically and chemically loadable at 20 °C after 7 days.

Abbreviations

h = hours

d = days

Product Information

Dolit^{LC}

BL.PH.001 | 04/12/2023



CRS
Chemical Resistant Systems

CLEANING

Tools that are soiled with uncured materials can be cleaned with Dolit-Universal-Cleaner. Clean only in well ventilated areas and observe safety measures.

SAFETY / DISPOSAL

- Ensure sufficient ventilation, especially when working in closed rooms, pits or containers.
- Observe fire and smoking ban.
- Observe safety data sheets, hazard statements and safety advice on the containers.
- Wear prescribed personal protective equipment. Avoid skin contact with the materials.
- Clean and care for hands with skin protection soap and ointment. Do not use solvents.
- Wear a dust mask during grinding work, e.g. repairs.
- Follow operating instructions according to §14 GefahrstoffV and Technical Rules for Hazardous Substances TRGS 507.
- Comply with the accident prevention regulations of the employers' liability insurance associations.
- Avoid direct contact of the materials with the flame, especially when welding, watch out for welding beads.
- Preferably consume residual quantities.
- Do not pour residues down the sink or into the dustbin.
- Collect residues for disposal separately in durable, sealable and labelled containers.

All information contained in this Product Information is based on the present state of our knowledge and practical experience. All data are approximate values for guidance only. A legally binding warranty of certain characteristics or the suitability for a certain purpose of use cannot be derived from this.

The information in this product information is our intellectual property. The Product Information sheet may neither be copied nor used by unauthorized parties, nor professionally distributed or otherwise made accessible to third parties without our prior consent.

This issue replaces all previous versions.